


What is claimed is:

1. A polyacrylate obtainable by thermal crosslinking of a polymer mixture comprising the following components:

5 a) a polyacrylate copolymer of the following monomers

a1) acrylates and/or methacrylates of the following formula



where $\text{R}^2 = \text{H}$ or CH_3 and R^1 is an alkyl chain with 1-20 carbon atoms,
at 65-99% by weight, based on a),

10 a2) olefinically unsaturated monomers containing functional groups,
at 0-15% by weight, based on a),

a3) acrylates and/or methacrylates whose alcohol component contains
tert-butoxycarbonyl (BOC) and/or hydroxyl groups,
at 1-20% by weight, based on a),

15 at 80-99.8% by weight, based on the polymer mixture of claim 1,

b) a polymerization regulating photoinitiator

at 0.1-15% by weight, based on the polymer mixture of claim 1,

c) difunctional isocyanate and/or bifunctional epoxide

at 0.1-5% by weight, based on the polymer mixture of claim 1.

20 2. The polyacrylate as claimed in claim 1, wherein

component b) is used at 0.5-1.5% by weight, based on the polymer mixture, and/or
component c) is used at 0.5-1% by weight, based on the polymer mixture.

25 ~~3. A process for preparing a crosslinked polyacrylate, wherein~~
the polymers to be crosslinked are first protected by introduction of tert-butoxycarbonyl
groups and the crosslinking takes place only after the deprotection, by thermal treatment
of the now deprotected polyacrylates.

30 ~~4. A process for preparing a crosslinked polyacrylate, wherein~~

the polymers to be crosslinked are first protected by introduction of tert-butoxycarbonyl groups and the crosslinking takes place only after the deprotection, by adding crosslinker substances and by thermal treatment of the now deprotected polyacrylates.

- 5 5. ^{according to claim 1} A process for preparing a crosslinked polyacrylate, wherein the polymers to be crosslinked are first protected by introduction of tert-butoxycarbonyl groups and the crosslinking takes place only after the deprotection, by adding difunctional or polyfunctional isocyanates and by thermal treatment of the now deprotected polyacrylates.

- 10 6. ^{polyacrylate according to claim 1} A process for preparing a crosslinked polyacrylate, wherein the polymers to be crosslinked are first protected by introduction of tert-butoxycarbonyl groups and the crosslinking takes place only after the deprotection, by adding difunctional or polyfunctional epoxides and by thermal treatment of the now deprotected polyacrylates.

7. ^{one of claims 36} The process as claimed in ~~any of the above claims~~ wherein the protective groups are eliminated by irradiation with UV light.

- 20 8. ^{claim 7} The process as claimed in ~~any of the above claims~~ wherein to eliminate the protective groups the polymer mixture is irradiated with ultraviolet light through a mask in such a way that only certain regions of the polymer mixture are exposed to the UV radiation.

- 25 9. The use of a polyacrylate of one of the above claims as a pressure-sensitive adhesive composition.

- 30 10. The use of a polyacrylate of one of the above claims as a pressure-sensitive adhesive composition for an adhesive tape, where the acrylic pressure-sensitive adhesive composition is present as a single- or double-sided film on a backing.

add
all